



360

Five-Minute Sandable Epoxy Adhesive

Description

Lord® 360 is a sag-resistant, high-performance, five-minute epoxy adhesive. The cured adhesive is sandable and paintable. Lord 360 is used in applications requiring rapid cure.

Features and Benefits

Easy-to-Use Packaging - available in Lord-Pak™ dispensing systems, reducing material waste and increasing productivity.

Contains No Solvent - 100% solids, nonflammable and virtually odorless.

Versatile - provides excellent adhesion to scuffed SMC, FRP, wood and other plastics.

Environmental Resistance - bonds assemblies which require resistance to high humidity, water, salt-spray and temperature extremes.

Easy Clean Up - uncured adhesive can be cleaned with detergent and water.

Typical Properties* of Uncured Lord 360 Adhesive

	Lord 360 Part A	Lord 360 Part B	Mixed
Appearance	Gray Paste	Off-White Paste	Gray Paste
Viscosity, cP @ 25°C (77°F) Brookfield HBF with Helipath @ 5 rpm	120,000 - 180,000	50 - 80,000	N/A
Density gram/cubic centimeter lb/gal	1.32 - 1.5 11.0 - 12.5	1.02 - 1.14 8.5 - 9.5	N/A N/A
Flash Point (closed cup)	>93°C (>200°F)	>93°C (>200°F)	>93°C (>200°F)
Total Solids Content by weight	100%	100%	100%
Working Time @ 24°C (75°F) 54g mass	N/A	N/A	2 minutes
Use Temperature	20°C - 38°C (68°F - 100°F)		
Mix Ratio by volume	1	1	N/A
Shelf Life from date of shipment at 25°C (77°F), unopened container	1 year	1 year	N/A

*Data is typical and not to be used for specification purposes.

Surface Preparation

Remove soil, grease, oil, fingerprints, dust, mold release agents, rust and other contaminants before applying Lord 360 adhesive.

In most cases, metal substrates which are free of oxidation need only an isopropyl alcohol wipe. Use an abrasive material to remove tarnish. Abrasion will also increase the substrate surface area and provide sites for physical bonding. Always follow abrasion by a second cleaning to ensure removal of loose particles.

Handle prepared surfaces carefully to avoid contamination. Assemble as soon as possible.

Mixing

Non-Automated

Measure each component to meet the mix ratio requirements. Thoroughly mix the components until uniform in color and consistency. Be careful not to whip excessive air into the adhesive.

Heat buildup due to an exothermic reaction between the two components will shorten the potlife of the adhesive. Mixing smaller quantities will minimize heat buildup. Do not use any adhesive that has begun to cure.

Automated

Lord 360 adhesive is packaged in Lord-Pak cartridge systems for convenient, automated mixing and application. Lord-Pak systems eliminate the waste involved in hand mixing and application without the capital investment of meter/mix/dispense equipment.

If the particular adhesive usage justifies the investment of M/M/D equipment, use positive displacement equipment. Consult your equipment supplier for details.

Application

Apply the mixed adhesive by spreading it on one or both of the substrates to be bonded using any convenient tool such as a stiff brush, spatula, or trowel. A paper cone can be used to apply the adhesive in a continuous bead. For general use, a film thickness of ~0.5 mm (0.020") is recommended. To control bondline thickness, a small amount of solid glass beads can be added into the mixed adhesive. This will also help minimize adhesive squeeze-out.

Join the part in such a way as to avoid entrapped air. Apply only enough pressure to ensure good wetting of Values stated in this bulletin represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Service Department.

Information provided herein is based upon tests believed to be reliable. Inasmuch as Lord Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Lord Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party including but not limited to any product end user. Nor does the company make any express or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use.

Lord is a registered trademark and Lord-Pak is a trademark of Lord Techmark, Inc., a subsidiary of Lord Corporation.
©Lord Corporation Printed in USA DS3381 (Rev. 2 7/04)

the adhesive on both substrates. Squeezing a little adhesive out at the edges is usually a sign of proper assembly. It is not necessary to clamp the assembly unless movement during adhesive setup is likely. Maximum adhesion will occur only with parts which mate well without the need for excessive clamping pressure during cure. Excessive clamping may squeeze too much adhesive from the bond area which can result in poor bond values.

Curing

Higher temperatures will provide faster cure rates; however, the bondline temperature should not exceed 162°C (325°F). Elevated temperature cure produces the highest bond strengths and impact resistance. Firm recommendations of cure times and temperatures are difficult to estimate because heat transmission varies according to material composition and heating methods.

At room temperature, the adhesive will cure fully in approximately 24 hours with handling strength in approximately 5 minutes, provided that the adhesive, substrates and ambient temperature are 18°C - 38°C (65°F - 100°F).

Storage

For maximum shelf life, ship and store Lord 360 adhesive in the original container at 4°C - 27°C (40°F - 80°F).

Clean Up

Uncured Adhesive

Clean up excess adhesive on the bonded assembly, as well as mixing and application equipment, before the adhesive sets up. Use hot water and detergent, or an organic solvent; ketones have been shown to work best.

Cured Adhesive

Removing cured Lord 360 adhesive is difficult because of its resistance to chemicals, solvents, and cleaning agents. Heat the adhesive to 204°C (400°F) or greater to soften the adhesive. This allows the parts to be separated and the adhesive to be more easily removed. Some success may be achieved with commercial epoxy strippers.

Subsequent Processing

After the adhesive has been cured, it may be filed, sanded, machined or otherwise handled in the same way as a light metal. Paints, lacquers, enamels, and other coatings may be applied without danger of solvent attack.

Cautionary Information

Before using this or any Lord product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

For information, contact Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
775-323-7542 fax 775-323-7595

LORD