



Accelerator 17

Accelerator for Acrylic Structural Adhesive

Description

Lord® Accelerator 17 is a mix-in curative used with acrylic adhesive resins. Lord Accelerator 17 curative is used with meter/mix/dispense equipment or prepackaged Lord-Pak™ cartridge systems. Lord Accelerator 17 is not a stand alone adhesive; it must be used with acrylic adhesive resins.

Features and Benefits

Convenient Cure Properties - cures at room temperature and can be used with all Lord acrylic adhesive resins.

Easy to Use - functions as a mix-in accelerator with Lord acrylic resins at a 10:1 mix ratio.

Contains No Solvent - provides 100% solids content, nonflammable, and virtually odorless.

Environmental Resistance - accompanies Lord acrylic adhesive resins to provide a bond which resists common environmental conditions.

Typical Properties* of Lord Accelerator 17 Curative

Appearance	Off-White liquid
Viscosity, cP Brookfield Model LVT Spindle #4 @ 12 rpm @ 25°C (77°F)	10,000 - 100,000
Density kg/m ³ lb/gal	1.15 - 1.39 9.6 - 10.4
Total Reactive Solids Content by weight	100%
Flash Point	>93°C (>200°F)
Shelf Life	Six months from date of shipment, 4°C - 27°C (40°F - 80°F), unopened container.

*Data is typical and not to be used for specification purposes.

Surface Preparation

See the product bulletin instructions for the adhesive being used with this accelerator.

Mixing

Mix-In

Confirm the proper mix ratio by consulting the technical bulletin for the Lord adhesive resin. Thoroughly mix the resin and accelerator components until uniform in color and consistency. Be careful not to whip excessive air into the adhesive.

Heat build-up due to an exothermic reaction between the two components will shorten the pot life of the adhesive. Mixing smaller quantities will minimize heat build-up. Do not use any adhesive that has begun to cure.

Automated

In conjunction with a Lord acrylic adhesive, Lord Accelerator 17 curative is packaged in Lord-Pak dual cartridge systems for convenient, automated mixing and application. Lord-Pak cartridge systems eliminate the waste involved in hand-mixing without the capital investment of meter/mix/dispense equipment. However, meter/mix/dispense equipment can be used when required.

Clean Up

Uncured - Clean up excess adhesive on the bond assembly, as well as the mixing and application equipment before the adhesive sets up. Use hot water and detergent or an organic solvent; ketones have been shown to work best.

Cured - Heat to 204°C (400°F) or higher to soften the adhesive. This will allow the parts to be separated and the adhesive to be more easily removed.

Values stated in this bulletin represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Service Department.

Information provided herein is based upon tests believed to be reliable. Inasmuch as Lord Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Lord Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party including but not limited to any product end user. Nor does the company make any express or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use.

Lord is a registered trademark and Lord-Pak is a trademark of Lord Techmark, Inc., a subsidiary of Lord Corporation.
©Lord Corporation Printed in USA DS3468 (Rev. 3 4/04)

Packaging

- 30 Ounce Tube
- 1/2 Pint Container (0.24 Liter)
- 1 Quart Container (0.95 Liter)
- 1 Gallon Container (3.8 Liter)
- 5 Gallon Pail (19 Liter)
- Convenient Cartridges

Storage

For maximum shelf life, ship and store Lord Accelerator 17 curative in the original container between 4°C - 27°C (40°F - 80°F). Optimum storage temperatures are between 4°C - 10°C (40°F - 50°F).

Cautionary Information

Before using this or any Lord product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

For information, contact Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
775-323-7542 fax 775-323-7595

LORD