



CA7700

Fast-Setting, High-Viscosity, Impact-Resistant, General Purpose, Cyanoacrylate Adhesive

Description

Lord® CA7700 adhesive is used to bond a variety of materials (i.e., plastic, wood, cork, and leather). Lord CA7700 adhesive qualifies for Mil-A-46050C Type II, Class 3 and CID A-A 3097, Type II, Class 3 approval.

Features and Benefits

Product Purity - contains no measurable trace of moisture contamination. Provides exceptionally consistent bond performance. Prevents settling, sedimentation and precure during storage.

Excellent Environmental Resistance - resists weathering and aging. Exhibits good performance at temperatures -60°C to 150°C (-76°F to 302°F).

Fast Cure - minimizes set-up time and reduces overall process time. Sets in 5 - 20 seconds when bonding plastic and rubber. Sets in 25 - 35 seconds when bonding metals.

Easy to Use - requires minimal user training. Provides consistent results from part to part.

Surface Preparation

Remove oil, grease, mold release, or other contaminants by pretreating with acetone, alcohol, ethyl acetate, or similar degreasing chemicals. Do not use any preparations which would cause the surface to become acidic, as this can slow adhesive cure.

Prior to bonding, clean elastomers with acetone. Roughen metal and plastic surfaces with sandpaper or by sand blasting. Machining of plastics (i.e., milling, drilling, or grinding) will remove adhesive repellents such as mold lubricants. This will allow for better wetting of the parts with the adhesive.

Special surface treatments such as flame treating or sodium etching are necessary for plastics such as polyethylene, polypropylene, polytetrafluoroethylene, polyacetal, and other fluorinated hydrocarbons. In cases where pretreatment is impractical, try using the adhesive without pretreatment.

Table 1: Typical Properties* of Uncured Lord CA7700 Adhesive

Appearance	Colorless liquid
Base Compound	Ethyl Cyanoacrylate
Viscosity, cP at 25°C (75°F)	700 - 1100
Density kg/m ³ lb/gal	1.05 9.0
Flash Point (TCC)	85°C (185°F)
Time to Handling Strength Plastic or Rubber Metal	5 - 20 seconds 25 - 35 seconds
Full Cure	24 hours
Shelf Life	6 months from date of shipment, @ 2°C - 7°C (35°F - 45°F), unopened container.

* Data is typical and not to be used for specification purposes.

Application

Apply Lord CA7700 adhesive by the drop. Maintain pressure while joining the parts.

Coverage is determined on the basis of the number of drops dispensed by a specific container. Use the information below as a general guideline:

Bottle Size	Drops/Bottle
14 gm	900
28 gm	1,800
56	3,600

Do not expose components to be bonded with Lord cyanoacrylate adhesive to aliphatic hydrocarbons and ester solvents. They will not resist alkalis and concentrated acids. Prolonged exposure to water or high humidity (>90% R.H.) will weaken the bond.

Curing

Actual setting times will be effected by factors such as temperature, humidity, glue line thickness and the mechanical and chemical nature of the surfaces to be bonded. Acidic surfaces retard polymerization, while alkaline surfaces accelerate polymerization.

Clean Up

Clean uncured adhesive with alcohol, acetone, or methyl ethyl ketone (MEK).

Packaging

- Bottles: 14-gram, 28-gram, 56-gram

Automatic dispensing equipment is available from outside vendors. Contact your Lord representative for recommended suppliers.

Storage

Store Lord CA7700 adhesive at 2°C - 7°C (35°F - 45°F). Bring to room temperature before using.

Cautionary Information

Before using this or any Lord product, refer to the Material Safety Data Sheet (MSDS) and label for safe use and handling instructions.

For industrial/commercial use only. Must be applied by trained personnel only. Not to be used in household applications. Not for consumer use.

Table 2: Typical Properties* of Cured Lord CA7700 Adhesive

Appearance	Colorless solid
Service Temperature Range	-60°C to 150°C (-76°F to 302°F)
Tensile Strength, Fe/Fe MPa (psi)	24.1 (3,495)

*Data is typical and not to be used for specification purposes.

Values stated in this bulletin represent typical values as not all tests are run on each lot of material produced. For formalized product specifications for specific product end uses, contact the Customer Service Department.

Information provided herein is based upon tests believed to be reliable. Inasmuch as Lord Corporation has no control over the manner in which others may use this information, it does not guarantee the results to be obtained. In addition, Lord Corporation does not guarantee the performance of the product or the results obtained from the use of the product or this information where the product has been repackaged by any third party including but not limited to any product end user. Nor does the company make any express or implied warranty of merchantability, or fitness for a particular purpose concerning the effects or results of such use.

Lord is a registered trademark of Lord Techmark, Inc., a subsidiary of Lord Corporation.
©Lord Corporation Printed in USA DS3486 (Rev.2 4/04)

For information, contact Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
775-323-7542 fax 775-323-7595

LORD