

TECHNICAL DATA

PR-1826 Class B Rapid Curing Fuel Tank Sealant

Description

PR-1826 Class B is a rapid cure, aircraft integral fuel tank sealant. It has a service temperature range from -80°F (-62°C) to 320°F (160°C), with intermittent excursions up to 420°F (216°C). This material is designed for fillet sealing of fuel tanks and other aircraft fuselage sealing applications. The cured sealant maintains excellent elastomeric properties after prolonged exposure to both jet fuel and aviation gas.

PR-1826 Class B is a two-part, epoxy cured Permapol® P-3 polythioether compound. The uncured material is a low sag, thixotropic paste, suitable for application by extrusion gun or spatula. Unlike standard polysulfide fuel tank sealants, it can cure at low temperatures and is unaffected by changes in relative humidity. This sealant has excellent adhesion to common aircraft substrates when correctly primed with PR-188 Adhesion Promoter.

The following tests are in accordance with AMS 3277 Type I Class B specification test methods.

Application Properties (Typical)

Color			
Part A	Black		
Part B	White		
Mixed	Dark gray		
Mixing ratio			
By weight	Part A:Part B 8.5:100		
Base viscosity			
(Brookfield #7 @ 2 rpm), Poise (Pa-s)	15,700 (1570)		
Slump, inches (mm)			
	Initial	50 Minutes	90 Minutes
B-1/4	0.25 (6.35)	_____	_____
B-1/2	0.25 (6.35)	_____	_____
B-2	0.20 (5.08)	0.35 (8.89)	0.50 (12.7)
Application life and cure time @ 77°F (25°C), 50% RH			
	Application life (hours)	Tack free time (hours)	Cure time to 30 A Durometer (hours)
B-1/4	1/4	<1	1.5
B-1/2	1/2	<2	3
B-2	2	<12	16

Performance Properties (Typical)

Cured 7 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.47
Nonvolatile content, %	96
Ultimate cure hardness, Durometer A	47
Peel strength, pli (N/25 mm), 100% cohesion, primed with PR-188 Adhesion Promoter	
AMS 2629 JRF immersion, 7 days @ 140°F (60°C)	
AMS 2471 (Anodized aluminum)	51 (227)
AMS 4901 (Titanium)	45 (200)
AMS 5516 (Stainless steel)	46 (205)
MIL-C-5541 (Alodine aluminum)	45(200)
MIL-C-27725 (IFT coating)	39 (174)
AMS 2629 JRF/NaCl-H ₂ O immersion, 7 days @ 140°F (60°C)	
AMS 2471 (Anodized aluminum)	59 (263)
AMS 4901 (Titanium)	58 (258)
AMS 5516 (Stainless steel)	56(249)
MIL-C-5541 (Alodine aluminum)	59 (263)
MIL-C-27725 (IFT coating)	55 (245)
Tensile strength, psi (KPa)	
Standard cure, 7 days @ 77°F (25°C), 50% RH	350 (2413)
Standard heat cycle	230 (1586)
Elongation, %	
Standard cure, 7 days @ 77°F (25°C), 50% RH	350
Standard heat cycle	225
Thermal rupture resistance - Retains pressure of 10 psi with only negligible deformation, both before and after immersion in AMS 2629 JRF.	
Low temperature flexibility @ -65°F (-54°C) - No cracking, checking or loss of adhesion.	
Corrosion resistance - No corrosion, adhesion loss, softening, or blistering after immersion in 2-layer salt water/ AMS 2629 JRF after 12 days @ 140°F (60°C) + 60 hours @ 160°F (71°C) + 6 hours @ 180°F (82°C).	
Resistance to hydrocarbons - 7 days @ 140°F (60°C) immersed in AMS 2629 JRF.	
Weight loss, %	2.0
Volume Swell, %	21
Flexibility - No cracks after bending 180 degrees over 0.125 inch (3.18 mm) mandrel.	

PR-1826 Class B Rapid Curing Fuel Tank Sealant

Repairability to itself - Excellent to both freshly cured as well as fuel aged and abraded fillets.

Resistance to other fluids - Excellent resistance to water, alcohols, petroleum-base and synthetic lubricating oils, and petroleum-base hydraulic fluids.

Fungus resistance

Non-nutrient

Shaving and sanding - No rolling or tearing

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface Preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth conforming to AMS 3819. (Reclaimed solvents or tissue paper should not be used.) Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

After the surface has been cleaned, apply PR-188 Adhesion Promoter with a clean brush or a gauze pad. Care must be taken to obtain a uniform thin coat. At standard temperature, allow the adhesion promoter to dry 30 minutes. It is not recommended to apply adhesion promoter below 45°F (7°C). The sealant must be applied within 8 hours of the application of the adhesion promoter. If this time is exceeded, the surface should be re-cleaned and the adhesion promoter reapplied. Do not use adhesion promoter if it contains particles or precipitate.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

Packing Options

PR-1826 Class B is supplied in a Semkit® package or pre-mixed and frozen cartridge. See the container for specific mixing instructions.

Storage Life

The storage life of PR-1826 Class B is at least 9 months when stored at temperatures below 80°F (27°C) in original, unopened containers. For pre-mixed and frozen cartridges the storage life is at least 30 days at -80°F (-63°C) or below.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

Additional information can be found at:
www.bergdahl.com

For sales and ordering information call
775-323-7542

Permapol and Semkit are trademarks of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

Authorized Distributor:
Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
775-323-7542
www.bergdahl.com

Issue Date: 06/10
Supersedes: 09/09
Lit: 0308