

TECHNICAL DATA

PR-2200 Class B Electrically Conductive Sealant

Description

PR-2200 Class B is an electrically conductive, rapid cure, corrosion inhibitive sealant. It has a service temperature range from -67°F (-55°C) to 250°F (121°C), with intermittent excursions up to 360°F (182°C). The cured sealant provides excellent electrical conductivity and EMI/RFI shielding effectiveness. This material acts as an effective barrier against the common causes of corrosion on aluminum alloys or between dissimilar metals. The cured sealant is resistant to exposure to both jet fuel and aviation gas.

PR-2200 Class B is a two part, nickel filled, epoxy cured, Permapol® P-3.1 polythioether compound. The uncured material is a low sag, thixotropic paste suitable for application by extrusion gun or spatula. This sealant has excellent adhesion to common aircraft substrates when correctly primed with PR-182 Adhesion Promoter.

The following tests are in accordance with Boeing St. Louis MMS-327 specification test methods.

Application Properties (Typical)

Color			
Part A	Black		
Part B	Gray		
Mixed	Black		
Mixing ratio		Part A:Part B	
By weight		6.58:100	
Slump, inches (mm)			
	Initial	50 Minutes	90 Minutes
B-1/2	0.38 (9.65)	N/A	N/A
B-1	0.5 (12.7)	0.5 (12.7)	0.4 (10.16)
Application life and cure time @ 77°F (25°C) and 50% RH			
	Application life (hours)	Tack free time (hours)	Cure time to 30 A Durometer (hours)
B-1/2	1/2	<3	3
B-1	1	<5	6

Performance Properties (Typical)

Standard cure 7 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.98
Nonvolatile content, %	97
Ultimate cure hardness, Durometer A	75
Shear strength, psi (KPa)	185 (1276)
Tensile strength, psi (KPa)	180 (1240)
Elongation, %	100
Electrical contact resistance, ohms	0.16
Volume/Bulk resistivity (Alessi four point probe), ohm-cm	
Standard cure, 7 days @ 250°(121°C)	0.20
7 days immersion in JRF @ 77°F (25°C) + 4 days @ 140°F(60°C)	0.35
Volume shrinkage, %	7
Corrosion resistance - No corrosion or significant change of conductivity after 2000 hours salt spray.	
Low temperature brittleness @ -65°F (-54°C) - No cracking or fractures.	

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface Preparation

Immediately before applying sealant to substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using appropriate solvents and a new-lint free cloth conforming to AMS 3819. (Reclaimed solvents or tissue paper should not be used.) Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

PR-2200 Class B Electrically Conductive Sealant

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

After the surface has been cleaned, apply PR-182 Adhesion Promoter with a clean brush or a gauze pad. Care must be taken to obtain a uniform thin coat. At standard temperature, allow the adhesion promoter to dry 30 minutes. It is not recommended to apply adhesion promoter below 45°F (7°C). The sealant must be applied within 8 hours of the application of the adhesion promoter. If this time is exceeded, the surface should be re-cleaned and the adhesion promoter reapplied. Do not use adhesion promoter if it contains particles or precipitate.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

Packing Options

PR-2200 Class B is supplied in a two-part Semkit® package or pre-mixed and frozen cartridge. See container for mixing instructions.

Storage Life

The storage life of PR-2200 Class B in a Semkit® package is at least 9 months when stored at temperatures below 80°F (27°C) in original, unopened containers.

The storage life of PR-2200 Class B Pre-mixed and frozen cartridges is a maximum of 30 days when stored at temperatures of -80°F (-62°C) or below.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

For emergency medical information call 1-800-228-5635.

Additional information can be found at: **www.bergdahl.com**

For sales and ordering information call **775-323-7542**

Permapol and Semkit are trademarks of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

Authorized Distributor:
Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
775-323-7542
www.bergdahl.com

Issue Date: 09/09
Supersedes: 06/09
Lit: 0086