

# TECHNICAL DATA

## PR-2007 Class B 1.1 Specific Gravity Fuel Tank Sealant

### Description

PR-2007 Class B is a 1.1 specific gravity, fast curing, high temperature aircraft integral fuel tank sealant. This material is designed for fillet sealing of fuel tanks and other aircraft fuselage sealing applications. It offers as much as a thirty percent weight savings, per unit volume, over traditional sealants used for similar purposes. The cured sealant maintains excellent elastomeric properties after prolonged exposure to aircraft fuels both jet fuel and aviation gas, and will resist limited contact to diphosphate ester based hydraulic fluids.

PR-2007 Class B is a two-part, manganese dioxide cured liquid polysulfide polymer compound. The uncured material is a low sag, thixotropic paste suitable for application by extrusion gun or spatula. It cures at room temperature to form a resilient sealant having excellent adhesion to common aircraft substrates.

The following tests are in accordance with AMS-3281 Type II specification test methods.

### Application Properties (Typical)

Color			
Part A	Dark Brown		
Part B	Off white		
Mixed	Dark brown		
Mixing ratio, By weight		Part A:Part B	
B-1/2	12:100		
B-2	10:100		
Base viscosity (Brookfield #7 @ 2 rpm), Poise (Pa-s)		10,000 (1,000)	
Slump, inches (mm)			
	Initial	50 Minutes	90 Minutes
B-1/2**	0.10 (2.54)	_____	_____
B-2	0.10 (2.54)	0.10 (2.54)	0.10 (2.54)
Application life and cure time @ 77°F (25°C), 50% RH			
	Application life (hours)	Tack free time (hours)	Cure time to 35 A Durometer (hours)
B 1/2	1/2	4	6
B-2	2	<6	8
**B1/2 pending qualification			

### Performance Properties (Typical)

Service temperature range	
-65°F (-54°C) to 250°F (121°C)	
Intermittent excursions 360°F (182°C) Max.	
Cured 14 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.1
Nonvolatile content, %	92
Ultimate cure hardness, Durometer A	45
Peel strength, pli (N/25 mm), 100% cohesion	
AMS 2629 immersion , 7 days @ 140°F (60°C)	
MIL-C-5541 (Alodined Al)	27(119)
AMS 2471 (Anodized Al)	36(158)
AMS 5516(Stainless Steel)*	40(176)
AMS 4911(Titanium )*	32(140)
AMS-C-27725 (IFT Coating)	32(140)
AS 4/3501-6 (Graphite/Epoxy)	31(136)
IM 7/5250-4 (Graphite/BMI)	28(123)
3% NaCl-H2O/AMS 2629, 7 days @ 140°F (60°C)	
MIL-C-5541 (Alodined Al)	31(136)
AMS 2471 (Anodized Al)	39(171)
AMS 5516(Stainless Steel)*	39(171)
AMS 4911(Titanium )*	36(158)
AMS-C-27725 (IFT Coating)	33(145)
AS 4/3501-6 (Graphite/Epoxy)	36(158)
IM 7/5250-4 (Graphite/BMI)	32(140)
AMS 3281 Fuel/Saltwater Heat Cycle	
MIL-C-5541 (Alodined Al)	37(162)
AMS 2471 (Anodized Al)	46(202)
AMS 5516(Stainless Steel)*	43(189)
AMS 4911(Titanium )*	39(171)
AMS-C-27725 (IFT Coating)	33(145)
AS 4/3501-6 (Graphite/Epoxy)	36(158)
IM 7/5250-4 (Graphite/BMI)	34(149)
*Primed with AMS3100 adhesion promoter.	
Tensile strength, psi (KPa)	
Standard cure, 14 days @ 77°F (25°C), 50% RH	
	268(1848)
14 days immersion in JRF @ 140°F (60°C)	
	239(1648)
Elongation, %	
Standard cure, 14 days @ 77°F (25°C), 50% RH	
	418
14 days immersion in JRF @ 140°F (60°C)	
	305
Low temperature flexibility @ -65°F (-54°C)	
No cracking, checking or loss of adhesion.	

# PR-2007 Class B 1.1 Specific Gravity Fuel Tank Sealant

Resistance to hydrocarbons - 7 days @ 140°F (60°C)  
immersed in JRF

Weight loss, % 4.7

Flexibility - No cracks after bending 180 degrees over  
0.125 inch (3.18 mm) mandrel.

Repairability to itself - Excellent to both freshly cured  
as well as fuel aged and abraded fillets.

Resistance to other fluids - Excellent resistance to  
water, alcohols, petroleum-base and synthetic lubri-  
cating oils, and petroleum-base hydraulic fluids.

Shaving and sanding - No rolling or tearing

**Note:** The application and performance property val-  
ues above are typical for the material, but not intend-  
ed for use in specifications or for acceptance inspec-  
tion criteria because of variations in testing methods,  
conditions and configurations.

## Surface Preparation

Immediately before applying sealant to primed sub-  
strates, the surfaces should be cleaned with solvents.  
Contaminants such as dirt, grease, and/or processing  
lubricants must be removed prior to sealant applica-  
tion.

A progressive cleaning procedure should be employed  
using appropriate solvents, and a new, lint-free cloth  
conforming to AMS 3819. (Reclaimed solvents or tis-  
sue paper should not be used). Always pour solvent  
on the cloth to avoid contaminating the solvent sup-  
ply. Wash one small area at a time.

It is important that the surface is dried with a second  
clean cloth prior to the solvent evaporating to prevent  
the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can  
affect sealant adhesion. It is recommended that  
adhesion characteristics to a specific substrate be  
determined prior to application on production parts  
or assemblies.

For a more thorough discussion of proper surface  
preparation, please consult the SAE Aerospace  
Information Report AIR 4069. This document is avail-  
able through SAE, 400 Commonwealth Avenue,  
Warrendale, PA 15096-0001.

## Packing Options

PR-2007 Class B is supplied in a two-part Semkit®  
package and Pre-mixed and frozen cartridge.

## Storage Life

The standard storage life of PR-2007 Class B in a  
Semkit® package is at least 9 months when stored at  
temperatures between 40°F (4.5°C) and 80°F (27°C)  
in original, unopened containers.

The storage life of PR-2007 Class B Pre-mixed and  
frozen is 28 days when stored at temperatures of  
-40°F (-40°C) or below.

## Health Precautions

This product is safe to use and apply when recom-  
mended precautions are followed. Before using this  
product, read and understand the Material Safety  
Data Sheet (MSDS), which provides information on  
health, physical and environmental hazards, handling  
precautions and first aid recommendations. An MSDS  
is available on request. Avoid overexposure. Obtain  
medical care in case of extreme overexposure.

**For industrial use only. Keep away from children.**

**For emergency medical information call  
1-800-228-5635.**

**Additional information can be found at:  
[www.bergdahl.com](http://www.bergdahl.com)**

**For sales and ordering information call  
775-323-7542**

Semkit is a trademark of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

Authorized Distributor:  
Bergdahl Associates, Inc.  
2990 Sutro Street  
Reno, Nevada 89512-1616  
775-323-7542  
[www.bergdahl.com](http://www.bergdahl.com)

Issue Date: 09/09  
Supersedes: 03/09  
Lit# 3094