

TECHNICAL DATA

PR-2870 Class C-12/24 Non-Chromate Corrosion Inhibitive Sealant

Description

PR-2870 Class C-12/24 is a non-chromate corrosion inhibitive fay surface sealant. It has a service temperature range from -80°F (-62°C) to 250°F (121°C), with intermittent excursions up to 300°F (149°C). This material acts as an effective corrosion inhibitor when used with aluminum alloys or with dissimilar metals. The cured sealant maintains elastomeric properties after limited exposure to both jet fuel and aviation gas.

PR-2870 Class C-12/24 is a two-part, epoxy cured Permapol® P-3.1 polythioether compound. The uncured material is a roller-grade liquid suitable for application by brush, extrusion gun or spatula. It cures at room temperature to form a resilient sealant having excellent adhesion to common aircraft substrates.

PR-2870 C-12/24 is unique in that while it possesses a long application and assembly time, it then exhibits rapid cure. This means that one product has the potential to be used in place of C-8, C-12, in addition to C-24, allowing for reduced inventory.

The following tests are in accordance with MIL-PRF-81733 Type IV, Class 2, Grade B test methods.

Application Properties (Typical)

Color		
Part A		Black
Part B		White
Mixed		Gray
Mixing ratio		
By weight	Part A:Part B	19.7:100
Base viscosity		
(Brookfield #7 @ 2 rpm),		
Poise (Pa-s)		2000 (200)
Application life and cure time @ 77°F (25°C), 50% RH		
		Cure time
Application	Assembly	to 30 A
life	time	Durometer
(hours)	(hours)	(hours)
24	48	96

PR-2870 Class C-12/24 meets the application requirements for C-8, C-12 and C-24.

Performance Properties (Typical)

Cured 14 days @ 77°F (25°C), 50% RH	
Cured specific gravity	1.48
Nonvolatile content, %	99
Ultimate cure hardness,	
Durometer A	51
Peel Strength, pli, Cohesive Failure	
48 hours @ 140°F in MIL-PRF-83282 (Hydraulic Fluid)	
MIL-C-81706 (Alodine)	55, 100%
MIL-A-8625 (Anodized)	62, 100%
QQ-P-416 (Cadmium-plated steel)	68, 100%
AMS4376 (Alodine magnesium)	60, 100%
MIL-T-9046 (Titanium C)	47, 100%
MIL-PRF-23377 (std. cure) (Epoxy primer)	51, 100%
48 hours @ 140°F in MIL-PRF-7808 (Lubricating Oil)	
MIL-C-81706 (Alodine)	56, 100%
MIL-A-8625 (Anodized)	40, 100%
QQ-P-416 (Cadmium-plated steel)	69, 100%
AMS4376 (Alodine magnesium)	52, 100%
MIL-T-9046 (Titanium C)	50, 100%
MIL-PRF-23377 (std. cure) (Epoxy primer)	51, 100%
48 hours @ 140°F in MIL-PRF-23699 (Lubricating Oil)	
MIL-C-81706 (Alodine)	59, 100%
MIL-A-8625 (Anodized)	60, 100%
QQ-P-416 (Cadmium-plated steel)	86, 100%
AMS4376 (Alodine magnesium)	39, 100%
MIL-T-9046 (Titanium C)	47, 100%
MIL-PRF-23377 (std. cure) (Epoxy primer)	61, 100%
48 hours @ 140°F in 3% NaCl	
MIL-C-81706 (Alodine)	37, 100%
MIL-A-8625 (Anodized)	38, 100%
QQ-P-416 (Cadmium-plated steel)	47, 100%
AMS4376 (Alodine magnesium)	54, 100%
MIL-T-9046 (Titanium C)	48, 100%
MIL-PRF-23377 (std. cure) (Epoxy primer)	52, 100%
48 hours @ 140°F in AMS 2629 (JRF)	
MIL-C-81706 (Alodine)	47, 100%
MIL-A-8625 (Anodized)	23, 100%
QQ-P-416 (Cadmium-plated steel)	29, 100%
AMS4376 (Alodine magnesium)	34, 100%
MIL-T-9046 (Titanium C)	21, 100%
MIL-PRF-23377 (std. cure) (Epoxy primer)	36, 100%
Tensile strength, psi (KPa)	
Standard cure, 14 days	
@ 77°F (25°C), 50% RH	400 (2760)

PR-2870 Class C-12/24 Non-Chromate Corrosion Inhibitive Sealant

Elongation, %

Standard cure, 14 days
@ 77°F (25°C), 50% RH 430

Low temperature flexibility @ -80°F (-62°F) - No cracking, checking or loss of adhesion.

Salt spray (fog) test for 670 hrs. (ASTM B117) - No corrosion to base substrate or deterioration of sealant.

Fungus resistance Non-nutrient

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

Surface Preparation

Immediately before applying sealant to primed substrates, the surfaces should be cleaned with solvents. Contaminants such as dirt, grease, and/or processing lubricants must be removed prior to sealant application.

A progressive cleaning procedure should be employed using appropriate solvents and a new lint-free cloth conforming to AMS 3819. (Reclaimed solvents or tissue paper should not be used.) Always pour solvent on the cloth to avoid contaminating the solvent supply. Wash one small area at a time.

It is important that the surface is dried with a second clean cloth prior to the solvent evaporating to prevent the redeposition of contaminants on the substrate.

Substrate composition can vary greatly. This can affect sealant adhesion. It is recommended that adhesion characteristics to a specific substrate be determined prior to application on production parts or assemblies.

For a more thorough discussion of proper surface preparation, please consult the SAE Aerospace Information Report AIR 4069. This document is available through SAE, 400 Commonwealth Avenue, Warrendale, PA 15096-0001.

Packing Options

PR-2870 Class C-12/24 is supplied in a two-part Semkit package or pre-mixed and frozen cartridge.

Storage Life

The storage life of PR-2870 Class C-12/24 is at least 9 months when stored at temperatures between 40°F (4°C) and 80°F (27°C) in original, unopened containers.

The storage life of PR-2870 Class C-12/24 in pre-mixed and frozen cartridges is at least 42 days when stored at temperatures below -80°F (-62°C).

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

For emergency medical information call 1-800-228-5635.

Additional information can be found at: www.bergdahl.com

For sales and ordering information call +1 775 323-7542

Desoprime is a trademark of PRC-DeSoto International Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in the U.S.A.

Authorized Distributor:
Bergdahl Associates, Inc.
2990 Sutro Street
Reno, Nevada 89512-1616
phone +1 775 323-7542
www.bergdahl.com

Issue Date: 03/16
Supersedes: 01/15
Lit: 4371