

TECHNICAL DATA

PR-1547 Potting And Molding Compound

Description

PR-1547 is a high hardness potting and molding compound. It has a service temperature range from -70°F (-57°C) to 300°F (149°C). This material is designed for applications where resistance to cold flow, high tensile strength and excellent electrical properties are required.

PR-1547 is a two-part, chemically curing polyurethane compound. It cures at 180°F (82°C) to a tough, semiflexible, cold flow-resistant rubber. The material has very good electrical properties, especially dielectric strength and volume resistivity, in thin films.

The following tests are in accordance with MIL-M-24041 and MIL-S-8516 specification test methods.

Application Properties (Typical)

Color			
Part A	Amber or Black		
Part B	Straw		
Mixed	Amber or Black		
Mixing ratio		Part A:Part B	
By weight	32:100		
Base viscosity			
(Brookfield #5 @ 10 rpm),			
Poise (Pa-s)			
two-part unit	250 (25)		
premixed and frozen (PMF)	450 (45)		
Application life to 2500 poise			
(250 Pa-s) @ 75°F (24°C), hours			
two-part unit	2		
premixed and frozen (PMF)	1		
	Tack free	Mold release	Cure time
	time	time	to 55 A
	(hours)	(hours)	Durometer
			(hours)
180°F (82°C)	2	3	7

Performance Properties (Typical)

Cured 16 hours @ 180°F (82°C)	
Cured specific gravity	1.05
Nonvolatile content, %	99
Ultimate cure hardness, Durometer A	80
Volume shrinkage, %	2.5
Tensile strength, psi (KPa)	3000 (20690)

Ultimate elongation, %	600
Tear strength (Die C), lbs./in.	250
Compression set	
(ASTM D 395, Method B), %	54
(ASTM D 395, Method A), %	7
Fungus resistance (MIL-E-5272)	Non-nutrient
Peel strength, pli (N/25 mm)	
Aluminum alloy*	40 (178)
Cadmium plate*	40 (178)
Neoprene**	25 (111)
Polyvinyl chloride***	20 (89)
*Primed with PR-420 Primer	
**Buffed and primed with PR-1523-M Adhesion promoter	
***Tackified with methyl ethyl ketone (MEK) and primed with PR-1543 Adhesion promoter	
Dielectric constant	
1 KHz @ 75°F (24°C)	5.8
1 MHz @ 75°F (24°C)	4.7
Power factor	
1 KHz @ 75°F (24°C)	0.050
1 MHz @ 75°F (24°C)	0.065
Volume resistivity, ohm-cm	
@ 75°F (24°C)	1 X 10 ¹³
@ 150°F (66°C)	5 X 10 ¹¹
@ 300°F (149°C)	5 X 10 ⁹
Surface resistivity, ohms	
@ 75°F (24°C)	1 X 10 ¹³
Insulation resistance, megohms	
@ 75°F (24°C)	200,000
@ 150°F (66°C)	10,000
@ 250°F (121°C)	500
Dielectric strength, volts/mil	
125 mils	300

Note: The application and performance property values above are typical for the material, but not intended for use in specifications or for acceptance inspection criteria because of variations in testing methods, conditions and configurations.

PR-1547 Potting And Molding Compound

Surface Preparation

Prepare surfaces according to the PR-1500 Series Potting/Molding Application Guide.

Packing Options

PR-1547 is supplied as a two-part unit or premixed and frozen Semco® cartridges.

Mixing Instructions

Mix according to the PR-1500 Series Potting/Molding Application Guide.

Storage Life

The storage life of PR-1547 in a two-part unit is at least 12 months when stored at temperatures below 80°F (27°C) in original, unopened containers. The storage life of PR-1547 in premixed and frozen Semco® cartridges is at least 30 days when stored at temperatures below -40°F (-40°C) in original, unopened containers.

Health Precautions

This product is safe to use and apply when recommended precautions are followed. Before using this product, read and understand the Material Safety Data Sheet (MSDS), which provides information on health, physical and environmental hazards, handling precautions and first aid recommendations. An MSDS is available on request. Avoid overexposure. Obtain medical care in case of extreme overexposure.

For industrial use only. Keep away from children.

**Additional information can be found at:
www.bergdahl.com**

**For sales and ordering information call
+1 775 323-7542.**

Semco is a trademark of PRC-DeSoto International, Inc., registered with the U.S. Patent Office.

All recommendations, statements, and technical data contained herein are based on tests we believe to be reliable and correct, but accuracy and completeness of said tests are not guaranteed and are not to be construed as a warranty, either expressed or implied. User shall rely on his own information and tests to determine suitability of the product for the intended use and assumes all risks and liability resulting from his use of the product. Seller's and manufacturer's sole responsibility shall be to replace that portion of the product of this manufacturer which proves to be defective. Neither seller nor manufacturer shall be liable to the buyer or any third person for any injury, loss, or damage directly or indirectly resulting from use of, or inability to use, the product. Recommendations or statements other than those contained in a written agreement signed by an officer of the manufacturer shall not be binding upon the manufacturer or seller.

Printed in U.S.A.

Bergdahl Associates, Inc
2990 Sutro Street
Reno, Nevada 89512-1616
+1 775 323-7542
www.bergdahl.com

Issue Date: 02/16
Supersedes: 11/15
Lit: 0390